



VICTREX® PEEK™ FILM TECHNOLOGY

APTIV® 1000 Series Films

Description

APTIV® 1000 series films are the unfilled semi-crystalline films made from VICTREX® PEEK™ polymer. The film provides a material solution for engineers in ultra-high performance applications.

APTIV films are a comprehensive range of versatile, high-performance films, the use of which can facilitate reduced systems costs, improved performance and enhanced design freedom.

APTIV 1000 has a unique combination of properties providing high temperature performance, light weight, mechanical strength, durability, excellent radiation, hydrolysis and chemical resistance, electrical insulation, wear and abrasion resistance, excellent barrier properties with high purity, good flammability without the use of flame retardants, low toxicity of combustion products, and low moisture absorption in a film format. Inherently halogen free and ease of processing makes APTIV films a technology enabler for our customers and end users.

Availability

The films are available in thicknesses from 12 microns up to 750 microns.

Applications

- Electrical insulation
- Pressure sensitive tapes
- Printed circuit substrates
- High temperature labels
- Washers in high speed motors
- Washers in mobile phone hinges
- Flexible surface heaters
- Aerospace insulation
- Pressure sensor membranes
- Acoustic speaker diaphragms and voice coils
- Capacitors
- Composites
- Proven temperature resistance to use of lead free solders


Certification

APTIV film is FDA and EU approved for food contact and is RoHS and 3A Sanitary Standards compliant.

Features

- High heat resistance
- Excellent tribological properties
- Broad chemical resistance
- Low moisture absorption
- High strength and toughness
- Stable, excellent electrical insulation properties
- Good flammability performance without use of flame retardant additives
- Inherently halogen free
- Radiation resistance
- Low smoke and toxic gas emission
- Excellent hydrolysis resistance
- Excellent barrier properties
- Excellent acoustic properties
- High purity
- Light weight
- Recyclable
- Easy to process – can be laminated to other materials, thermoformed, metallized, coated, printed, stamped and die cut, welded and heat sealed and coated.

Figure 1: Physical properties at 23°C (73°F) and 200°C (392°F) for APTIV 1000, 50 microns (ISO 527)



Standard Thicknesses and Widths

The standard width for film is 610 mm – widths up to 1450 mm available upon request.

Standard thicknesses available (in microns) — 12, 18, 25, 50, 75, 100, 125, 150, 200, 250, 300, and 500.

Please inquire for other thicknesses up to 750 microns.

Standard thickness tolerance is better than +/-7%

Surface Finishes

Standard surface finish is matte/gloss, although gloss/gloss is available on request. Typical Ra values can be supplied on request.

Custom Finishing (Slitting and Surface Treatment)

The slitter capability in the APTIV film facility allows custom lengths and widths down to 45 mm to be produced. Widths below 45mm are available on request. Surface treatment by atmospheric plasma process of the film is also available by request taking the surface energy of the treated APTIV film surface to greater than 55 dynes per cm. (A minimum order quantity or value applies.)

Mechanical Properties at Various Thicknesses

ISO 527 at 23°C (73°F)

		25μ	50μ	125μ	250μ
Tensile Strength	MPa	130	120	110	100
Modulus	GPa	3.0	2.8	2.4	2.2
Elongation at break	%	>150	>150	>150	>150

Electrical Properties at Various Thicknesses

ATSM D149, 23°C (73°F), 1/4 inch electrode

		25μ	50μ	125μ	250μ
Dielectric Strength	kV/mm	270	190	120	70
Breakdown Voltage	kV	6.75	9.5	15	17.5

APTIV 1000 acts as an excellent electrical insulator across a wide range of temperatures and electrical frequencies.

Packaging and Storage

APTIV film is supplied in roll form on either 3" or 6" high quality, resin coated and polished fiber cores. These cores are a Class A standard core. APTIV film is very stable and will retain its properties for several years when stored in the original packaging in a frost free environment up to 50°C (122°F). APTIV film is unaffected by humidity and is unaffected by moisture. The rolls should be stored in a weathertight facility so that the packaging is not damaged.

Disposal

APTIV film is classed as a non-hazardous material and can be disposed of by landfill.

Labelling of Products

All products are packaged using robust and purpose designed packaging, and are fully labelled to comply with national and international standards. Labels indicating grade, unique batch number, roll length, roll width, product thickness, and net weight will be affixed to the outer packaging and the core.

Units of Sale

Orders for APTIV film should be placed in kilograms or imperial pounds.

Property	Test Method	Test Condition	Units	1000-050 (50 micron)
Tensile Modulus	ISO 527	23°C	GPa	2.8
Tensile Strength (at break)	ISO 527	23°C	MPa	120
Tensile Elongation (at break)	ISO 527	23°C	%	>150
Puncture Strength	Def Stan 81-75	23°C	kJ/m ²	26
Tear Strength	ISO 6383-1	23°C	N/mm	6.7
Shrinkage	TM-VX-84	200°C	%	<2
Specific Gravity	ISO 1183	23°C		1.30
Water Absorption (50% RH)	ISO 62	23°C, 24h	%	0.04
Coefficient of Linear Thermal Expansion	ASTM D696	MD, below Tg	ppm	47
Dielectric Strength	ASTM D149	23°C, 1/4 inch electrode	kV/mm	190
Volume Resistivity	ASTM D257	100V, 23°C	Ohm cm	4 x 10 ¹⁶
Dielectric Constant	ASTM D150	23°C, 10 MHz		3.5
Loss Tangent	ASTM D150	23°C, 10 MHz		0.002

Compliances

APTIV 1000 film is approved for Food Contact Use:

- APTIV 1000 film is compliant with the compositional requirements of FDA 21 CFR 177.2415.
- APTIV 1000 film is compliant with the framework regulation (EC) No. 1935/2004/EC and commission directive 2002/72/EC and the amendments up to 2005/79/EC.
- APTIV 1000 film is fully compliant with the 3-A Sanitary Standards.

APTIV 1000 film complies with the requirements of RoHS European Directive 2002/95/EC and can be used to manufacture products compliant with the same directive.

APTIV 1000 film is inherently halogen free in accordance with IEC61249-2-21.

Secondary Processes

APTIV 1000 film can easily be subjected to a range of secondary process operations, which allow designers and engineers to obtain the benefits of APTIV film properties in a variety of forms.

- Surface treatment
- Adhesion
- Coatings
- Heat welding and heat sealing
- Metallization
- Laser marking and machining
- Slitting
- Die cutting and stamping
- Thermal lamination
- Thermoforming
- Printing

www.aptivfilms.com



Victrex plc is the leading global manufacturer of Polyaryletherketones, high-end polymers, which are sold under the brand names VICTREX® PEEK™, VICTREX® PEEK-HT™, VICTREX® T-Series™, VICOTE® and APTIV®. With production facilities in the UK backed by sales and distribution centres serving more than 30 countries worldwide, our global market development, sales, and technical support services work hand-in-hand with customers offering practical assistance in the areas of processing, design and application development. Contact us today to find out how we can help you.



World Headquarters

Victrex plc
Hillhouse International
Thornton Cleveleys
Lancashire FY5 4QD
United Kingdom
Tel: + (44) 1253 897700
Fax: + (44) 1253 897701
Email: victrexplc@victrex.com

Americas

Victrex USA Inc
300 Conshohocken State Road
Suite 120
West Conshohocken, PA 19428
USA
Tel: + (1) 800-VICTREX
Tel: + (1) 484-342-6001
Fax: + (1) 484-342-6002
Email: americas@victrex.com

Europe

Victrex Europa GmbH
Langgasse 16
65719 Hofheim/Ts.
Germany
Tel: + (49) 6192 96490
Fax: + (49) 6192 964948
Email: eurossales@victrex.com

Asia Pacific

Victrex Japan Inc
Hanai Building 6F
1-2-9 Shiba-Kouen
Minato-ku
Tokyo 105-0011
Japan
Tel: + (81) 35777 8737
Fax: + (81) 35777 8738
Email: japansales@victrex.com

Asia Pacific

Victrex High Performance
Materials (Shanghai) Co Ltd
Part B Building G
No. 1688 Zhuanxing Road
Xinzhuang Industry Park
Shanghai 201108
China
Tel: + (86) 21-6113 6900
Fax: + (86) 21-6113 6901
Email: scsales@victrex.com

©Victrex plc

VICTREX PLC BELIEVES THAT THE INFORMATION CONTAINED IN THIS BROCHURE IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS AND/OR USES OF THE PRODUCT OR PRODUCTS, BUT IT IS THE CUSTOMER'S RESPONSIBILITY TO THOROUGHLY TEST THE PRODUCT IN EACH SPECIFIC APPLICATION TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY FOR EACH END-USE PRODUCT, DEVICE OR OTHER APPLICATION. SUGGESTIONS OF USES SHOULD NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PARTICULAR PATENT. THE INFORMATION AND DATA CONTAINED HEREIN ARE BASED ON INFORMATION WE BELIEVE RELIABLE. MENTION OF A PRODUCT IN THIS DOCUMENTATION IS NOT A GUARANTEE OF AVAILABILITY. VICTREX PLC RESERVES THE RIGHT TO MODIFY PRODUCTS, SPECIFICATIONS AND/OR PACKAGING AS PART OF A CONTINUOUS PROGRAM OF PRODUCT DEVELOPMENT. VICTREX® IS A REGISTERED TRADEMARK OF VICTREX MANUFACTURING LIMITED. PEEK™, APTIV™, PEEK-ESD™, T-SERIES™, PEEK-HT™ AND ST™ ARE TRADEMARKS OF VICTREX PLC. VICOTE® IS A REGISTERED TRADEMARK OF VICTREX PLC.

THE USE OF TM ON THE OTHER MARKS IS ACCEPTABLE, IRRESPECTIVE OF WHETHER VICTREX PLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, A WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR OF INTELLECTUAL PROPERTY NON-INFRINGEMENT, INCLUDING, BUT NOT LIMITED TO PATENT NON-INFRINGEMENT, WHICH ARE EXPRESSLY DISCLAIMED, WHETHER EXPRESS OR IMPLIED, IN FACT OR BY LAW. FURTHER, VICTREX PLC MAKES NO WARRANTY TO YOUR CUSTOMERS OR AGENTS, AND HAS NOT AUTHORIZED ANYONE TO MAKE ANY REPRESENTATION OR WARRANTY OTHER THAN AS PROVIDED ABOVE. VICTREX PLC SHALL IN NO EVENT BE LIABLE FOR ANY GENERAL, INDIRECT, SPECIAL, CONSEQUENTIAL, PUNITIVE, INCIDENTAL OR SIMILAR DAMAGES, INCLUDING WITHOUT LIMITATION, DAMAGES FOR HARM TO BUSINESS, LOST PROFITS OR LOST SAVINGS, EVEN IF VICTREX HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, REGARDLESS OF THE FORM OF ACTION.

